

TESTING PERFORMED AT CURTIN UNIVERSITY. PERTH. WEST AUSTRALIA.

Table 'D' Oven - 55 deg C

Specimen Name	Breadth(mm) (original)	Depth(mm) (original)	Length(mm) (original)	Breadth(mm) (after 2hrs)	Depth(mm) (after 2hrs)	Length(mm) (after 2hrs)	Breadth(mm) (after 48hrs)	Depth(mm) (after 48hrs)	Length(mm) (after 48hrs)	Weight (g)
7	75.90	86.20	76.00	76.10	86.30	76.10	76.10	86.40	76.00	95.67
8	76.00	86.30	76.00	76.10	86.40	76.10	76.10	86.40	76.20	96.48
*12	75.90	86.20	75.80	76.10	86.40	76.10	76.00	86.30	76.00	98.96

Table 'E' Oven - 105 deg C

Specimen Name	Breadth(mm) (after 55 deg)	Depth(mm) (after 55 deg)	Length(mm) (after 55 deg)	Breadth(mm) (after 2hrs)	Depth(mm) (after 2hrs)	Length(mm) (after 2hrs)	Breadth(mm) (after 24hrs)	Depth(mm) (after 24hrs)	Length(mm) (after 24hrs)	Weight (g)
7	75.90	86.10	75.90	74.00	85.10	73.60	72.60	84.70	72.90	95.67
8	76.00	86.20	75.90	74.10	85.40	74.10	72.20	84.60	73.20	96.48
*12	76.00	86.30	76.00	76.20	86.70	76.20	76.20	86.50	76.20	98.96

* denotes '2nd series' of tests

^ denotes '3rd series' of tests